

# Technical Data Sheet

## Filtration Products



### Attributes & Properties <sup>◇</sup>

Name:	PL1350A INTREPID® Filtration Media with Antimicrobial Additive
Color:	White
Basis Weight:	3.25 ounces per square yard Range 3.15 to 3.35 ounces per square yard (110 grams / square meter) Range 107 to 113 grams per square meter
Efficiency:	68.0 % Range 65% - 70% TSI Model 8130 automated filter tester with 0.1 µm count median diameter NaCl particles at 85 liters per minute.
Air Permeability:	Target: 280 cubic feet of air/minute per square foot of media (Range: 260-300 cubic meter of air / second per square meter of media) Textest FX 3300
Thickness:	0.06 - .08 inches
Inside Core Diameter:	6.75 inches (171 millimeters)

# Technical Data Sheet

## Filtration Products



### Attributes & Properties <sup>◇</sup>

#### PL1350A INTREPID® Filtration Media with Antimicrobial Additive

page 2

---

Roll Length:	900 linear yards (822.96 linear meters)
Roll Diameter:	42 inches (1066.8 millimeters) estimated
Slit Width Tolerance:	+1/8, -1/8 inch (+3 mm, -3 mm) Slit width tolerance measured at the outside of the roll, under tension.
Air Entering Side:	The air entering side of the filter media faces the core.
Packaging:	Cardboard headers, full stretch wrap coverage, multiple slit rolls of the same width may be packaged together into a Powerpack

#### Roll Labeling Information:

<u>Slit Roll Label</u>
Slit roll number
Product name and description
Production date
Basis weight
Slit width
Roll length
Roll weight
Country of origin

<u>Powerpack Label</u>
Powerpack number
Product name and description
Production date
Basis weight
Roll weight
Slit width
Total square yards in the powerpack
Total linear yards in the powerpack
Country of origin

Production Reference:  
Revision: DJ 7/16/2024

SPEC-32991

<sup>◇</sup> Unless otherwise noted, the material described in this document is available for commercial sale and sold with a limited warranty. Kimberly-Clark Corporation and/or Kimberly-Clark Worldwide retains all intellectual property rights to this material, including trademarks and trade names. If the material described is defined as developmental, the material properties are estimates only and are not warranted by Kimberly-Clark Corporation.